



26 Ga Steel Gutter Coil Specifications

MATERIALS

- A. All ACM Steel Galvanized Gutter Coils shall be made of a A653 CS(B) Galvanized coil sheet, or equivalent. The metal shall be treated on both sides with a non-chromate chemical conversion coating to ensure proper paint adhesion and resistance to corrosion. GGC31178 or GGC315 gutter coil product shall be coated on the front side with ACM’s baked on, high performance, Polykote® 3000 paint system that is specifically formulated for residential exterior applications. The backside of all gutter coils shall be coated with a full coat of Polyester backer finish unless specified otherwise. The nominal film thickness of Smooth coatings shall be a 0.9 to 1.0 DFT total front side and 0.9 to 1.0 DFT total White on the bottom.
- B. Physical Properties of Coated Surface:
 - a. Coated film hardness achieves F-2H pencil as tested per ASTM D3363
 - b. Solvent Resistance: 50 ~ 100+ MEK rubs as tested per ASTM D4752
 - c. Flexibility: Nominal 2-T180 NTO (subject to method of forming & metal thickness) as measured by ASTM D4145-83
 - d. Reverse Impact: 1.5X metal thickness NTO ASTM D2794

Accelerated Weathering:

- a. 5% Salt Spray (1000 hours) no creep over 1/32” from scribe ASTM B 117
- b. 100% Humidity: No significant visual change after 1,000 HR per ASTM D 2247-87
- c. QUV test as achieved by ASTM D4587 no visible loss of film integrity and no chalking greater than #8 after 500 HR, as measured by ASTM D 4214-89

- C. ACM gutter coil products are all packaged with one to three rolls per skid. Coil shall be of the widths, lengths, and thickness listed below:

<u>Product</u>	<u>Width</u>	<u>Weight/Coil</u>	<u>Nominal Thickness*</u>
GGC31178	11-7/8”	340 – 400 LBS	26 GA
GGC315	15”	350 – 550 LBS	26 GA

- D. ACM’s (26 GA) Steel Gutter Coil is available in a wide variety of colors to match ACM metal products, as well as most major manufacturers’. Please refer to color literature for color availability.

APPLICATIONS

ACM Steel Gutter Coil is designed for residential and light commercial applications. Gutter coil can be field formed to provide seamless gutter systems. Gutter system shall be attached per contractor’s direction.

CONSIDERATIONS

Corrosion is likely to happen with direct contact of steel product(s) to certain dissimilar materials or water run-off from same such materials. Care should be taken to avoid contact of steel with any corrosive materials during the installation process, including, but not limited to: concrete, stucco, pretreated lumber, corrosive chemicals, fiber cement products, masonry cement, roofing made with metallic granules of dissimilar metals (copper, zinc, aluminum, etc.), salt, and dissimilar metals.

ACM – Beloit
 1600 Park Avenue
 Beloit, WI 53511
 ph: 608.365.0296
 fax: 608.365.0493

ACM – Houston
 11615 Brittmooore Park Dr
 Houston, TX 77041
 ph: 713.466.1797
 fax: 713.466.5404

ACM – Apollo Beach
 6938 N US Hwy 41
 Apollo Beach, FL 33572
 ph: 813.671.3444
 fax: 813.671.5650

ACM - Lodi
 1307 E Pine St.
 Lodi, CA 95240
 ph: 209.334.1489
 fax: 209.334.4589