



## Aluminum Fascia Material Specs.

### MATERIALS

- A. All ACM Fascia Material Products shall be made of a 3105/3025-type aluminum coil sheet with a minimum tensile strength of 25,000 psi, or equivalent, as referenced in Aluminum Standards and Data, Table 7.1. The metal shall be treated on both sides with a non-chromate chemical conversion coating to ensure proper paint adhesion and resistance to corrosion. All Edge Metal and Flashing products shall be coated on both sides with ACM's baked on, high performance, Polykote® 3000 paint system that is specifically formulated for residential exterior applications. The backside of all Polykote® 3000 trim coil shall be coated with a full coat of Polykote® 3000 paint. The film thickness of Smooth coatings shall be a nominal 0.70 - 0.80 mils on each side. Whereas the film thickness of PVC coatings shall be a nominal 0.30 – 0.35 mils on the topside and 0.10 – 0.20 on the backer.
- B. All Aluminum Fascia Products shall be made of a nominal .024” thick aluminum material with a H26 hardness rating and a 1T180-3T180 flexibility.
- C. Recycled content of aluminum reaches up to 86%

### APPLICATIONS

ACM Aluminum Fascia Material is designed for exterior use on residential and light commercial applications. It is used in most applications for covering and protection of the wooden sub fascia material from water and exterior elements and corrosion.

### CONSIDERATIONS

Corrosion is likely to happen with direct contact of aluminum product(s) to certain dissimilar materials or water run-off from same such materials. Care should be taken to avoid contact of aluminum with any corrosive materials during the installation process, including, but not limited to: concrete, stucco, pretreated lumber, corrosive chemicals, fiber cement products, masonry cement, roofing made with metallic granules of dissimilar metals (copper, zinc, steel, etc.), salt, and dissimilar metals.

- The standard thickness tolerance for products made from aluminum sheet material shall be +0.000”, -0.003”.

ACM Beloit  
1600 Park Avenue  
Beloit, WI 53511  
ph: 608.365.0296  
fax: 608.365.0493

ACM Joplin  
2671 S. Kenser Road  
Joplin, MO 64801  
ph: 417.624.9140  
fax: 417.624.9143

ACM Houston  
11615 Brittmoore Park Dr.  
Houston, TX 77041  
ph: 713.466.1797  
fax: 713.166.5404

ACM Tampa  
5140 West Clifton Street  
Tampa, FL 33634  
ph: 813.884.0444  
fax: 813.881.1738