

## ARCHITECTURAL GUIDE SPECIFICATIONS

The following are parts of a guide specification for incorporation into architectural specifications. Complete details, specifications, and descriptive text for the installation of copper roofs, gutters, flashings, etc., are contained in the Revere manual *Copper & Common Sense*.

### General

#### QUALITY ASSURANCE

Unless otherwise shown or specified, comply with applicable recommendations and details in *Copper & Common Sense* by Revere Copper Products, Inc.

### Products

#### Material Data

##### Physical Properties

Atomic Wt.	63.54
Specific gravity	8.89 to 8.94
Density	0322lb./cu.in.
Coefficient of thermal expansion	0.0000098

Thickness	Theoretical	Minimum	Wt/Sq. Ft
16 oz.	0.0216"	0.0204"	1.00 lb.
20 oz.	0.0270"	0.0258"	1.25 lb.
24 oz.	0.0323"	0.0308"	1.50 lb.
32 oz.	0.0431"	0.0411"	2.00 lb.

	Mechanical Properties		Temper designation	
	060 Soft	H00 cold-rolled	H01 high yield	
Tensile strength	30-38	32-40	34-42	
Yield strength	-	20	28	
Elongation	45%	30%	25%	
Rockwell, F Scale	up to 65	54-82	60-84	

### MATERIALS

**A. Copper-** Select copper or coppers as required for aesthetics.

**1. Standard sheet copper:** cold rolled ounce weight (12-ounce, 16- ounce, 20-ounce, and /or 32-ounce as noted on drawings) copper sheet complying with ASTM B370. Unless otherwise noted, temper shall be H00.

**2. Pre-patinated copper:** cold rolled ounce weight (16-ounce, 20-ounce, and/or 24-ounce as noted on drawings) copper sheet complying with ASTM B882 and with the color and finish of Revere **EverGreen™**.

**3. Tin-zinc alloy coated copper:** cold rolled ounce weight (12-ounce, 16-ounce, 20-ounce as noted on drawings) copper coated both sides with tin-zinc alloy. Base copper sheet or coil shall comply with ASTM B370.

Finish and appearance shall be that of Revere **FreedomGray™**.

**4. Pan-forming copper:** cold rolled ounce weight (12-ounce, 16-ounce, and/or 20-ounce as noted on drawings) copper in coil complying with ASTM B370 and manufactured in accordance with specifications for Revere **Ultrapan™**.

**5. Textured copper:** Solid copper having a designated minimum copper content of 99.3% or higher, in thickness ranging from .008" to .135", as specified on drawings. Finish and appearance shall be that of Revere **Liberty Collection™ Rigidized®** textured copper.

**6. Copper composite panel:** Thermoplastic core coated both sides with lightweight copper sheet, with a protective film on exterior skin. Total thickness shall be 4mm or 6mm as specified on drawings. Finish and appearance shall be that of Revere **Alpolc Composite Panel™**.

**B. Solder-** shall conform to ASTM B32.

For **FreedomGray** tin/zinc alloy coated copper- Pure tin or lead-free, high-tin solders such as Number 497 by Johnson Manufacturing.

**C. Fasteners-** for plain copper, **EverGreen** pre-patinated copper and **FreedomGray** tin/zinc alloy coated copper shall be copper, copper alloy or non-magnetic, series 300 stainless steel.

### Execution

#### STORAGE AND COORINATION

**A.** Store all architectural copper sheet and coils (plain/bare, **EverGreen**, and/or **FreedomGray**) off the ground in an enclosed structure so as to maintain dry conditions and exclude condensation. Do **not** store on bare ground under tarp. Store **EverGreen** pre-patinated copper patinated side to patinated side (green to green).

**B.** Handle sheets and formed shapes in a manner to reduce scratches, dents, etc. Pad or tape tables, beds, brakes, and other surfaces over which **EverGreen** pre-patinated copper may be moved or placed during fabrication.

Note: The use of gloves may minimize fingerprints during initial weathering. Fingerprints fade and disappear with additional weathering. However, in arid locations they may persist for an extended period.

#### INSTALLATION

**A.** Except as otherwise shown or specified, comply with Revere Copper Products, Inc. recommendations and instructions as published in *Copper & Common Sense* and published Revere literature for **EverGreen** and/or **FreedomGray**.

**B.** Separate and protect dissimilar metals as recommended by manufacturers of dissimilar metals (other than copper).

**C.** Solder plain/bare copper, **EverGreen**, and/or **FreedomGray** in accordance with instructions published by Revere Copper Products, Inc.

*Note: Prior to soldering, plain/bare copper, EverGreen, and/or FreedomGray must be mechanically cleaned to produce a bright, unoxidized surface. Plain/bare copper and EverGreen should be pre-tinned before soldering. It is not necessary to remove the tin-zinc alloy coating from FreedomGray.*

#### CLEANING

Do **not** chemically or abrasively clean plain/bare copper, **EverGreen**, and/or **FreedomGray**. If necessary, construction dirt may be washed from copper with clean, fresh water only. Do **not** use soaps, detergents or other cleaning agents.

#### PROTECTION

Protect plain/bare copper, **EverGreen**, and/or **FreedomGray** from oils, greases, masonry cleaning compounds, iron and steel fines and fasteners, and other construction materials that may stain or discolor copper surface. To minimize condensation or water stains, at the end of each workday remove tarps or other protections placed on copper.

Manufacturing representatives are available for assistance or on-site meetings.

**Refer to current manufacturer's MSDS for safety and handling information.**



**Revere Copper Products, Inc**

One Revere Park, Rome, NY 13440-5561

For technical assistance:

1-800-448-1776 ext. 2474 or 2707

Fax: 315-338-2105

[www.reverecopper.com](http://www.reverecopper.com)

email:archcopper@reverecopper.com

Revere Liberty Collection, FreedomGray, EverGreen, Ultrapan and Revere Classic Copper are trademarks of Revere Copper Products, Inc.

Alpolc Composite Panel is a trademark of Mitsubishi Chemical America. Rigidized is a registered trademark of Rigidized Metals Corporation. ZT alloy is a trademark of Follansbee Steel's patented product.