



Galvalume® Drip Edge Specifications

MATERIALS

- A. GALVALUME® coatings are approximately 43% zinc, 55% aluminum, with the balance containing primarily silicon and iron for good coating adhesion.
- B. ACM GALVALUME® 26 gauge drip edges are available in various sizes and configurations.

APPLICATIONS

ACM GALVALUME® drip edge is designed for residential and light commercial applications. GALVALUME® drip edge shall be attached per contractor's direction and state and local building codes.

CONSIDERATIONS

Corrosion is likely to happen with direct contact of GALVALUME® product(s) to certain dissimilar materials or water run-off from these materials. Care should be taken to avoid contact of GALVALUME® product(s) with any corrosive materials during the installation process, including, but not limited to: concrete, stucco, pretreated lumber, corrosive chemicals, fiber cement products, masonry cement, roofing made with metallic granules of dissimilar metals (copper, zinc, aluminum, etc.), salt, and dissimilar metals.

- * Some products and colors may be limited to specific geographic distribution areas.

ACM – Beloit
1600 Park Avenue
Beloit, WI 53511
Ph: 877.279.5096
Fax: 608.365.0493

ACM – Shawnee
4124 Powell Drive
Shawnee, KS 66226
Ph: 877.279.5096
Fax: 608.365.0493

ACM – Apollo Beach
6938 N. Hwy 41
Apollo Beach, FL 33572
Ph: 800.749.4067
Fax: 608.364.0598

ACM – Houston
11615 Brittmoore Park Dr.
Houston, TX 77041
Ph: 800.357.7523
Fax: 713.466.5404

ACM – Lodi
1307 E. Pine Street
Lodi, CA 95240
Ph: 877.213.5962
Fax: 608.362.0599